

DIVERSIFIED

TESTING LABORATORIES, INC.

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
Phone (336) 227-7710 • Fax (336) 227-1175

April 16, 2003

Mr. Johnny Skinner
PHIFER WIRE PRODUCTS
P.O. Box 1700
Tuscaloosa, AL 35403

Reference: Laboratory Test Report
Lab Identification No. 6332
Invoice No. 9214 (Attached)

Dear Mr. Skinner:

One (1) sample, identified as **ARLYN SHADE MESH**, was received and tested in accordance with the National Fire Prevention Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 1999 Edition, (Test 2, Large Scale)". The results are as follows:

<u>Specimen Number</u>	<u>After Flame</u>	<u>Residual Flame</u>	<u>Char Length</u>
Folds 1	0.0	0.0	12.0
2	0.0	0.0	11.0
3	0.0	0.0	11.0
4	0.0	0.0	13.0


The fabric sample submitted meets the minimum requirements of the above standard. The length of char on the individual folded specimens shall not exceed 41.3 inches. Additionally, no specimen shall continue flaming for more than two (2) seconds after the test flame is removed and no residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Karon S. Matkins

KSM/mr
Attachment



DIVERSIFIED

TESTING LABORATORIES, INC.

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
Phone (336) 227-7710 • Fax (336) 227-1175

April 16, 2003

Mr. Johnny Skinner
PHIFER WIRE PRODUCTS
P.O. Box 1700
Tuscaloosa, AL 35403

Reference: Laboratory Test Report
Lab Identification No. 6332
Invoice No. 9214 (Attached)

Dear Mr. Skinner:

One (1) sample, identified as **ARLYN SHADE MESH**, was received and tested in accordance with the National Fire Prevention Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 1999 Edition, (Test 1, Small Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Residual Flame (seconds)</u>	<u>Weight Loss (percent)</u>
1	0.0	1.70
2	0.0	4.80
3	0.0	2.84
4	0.0	4.82
5	0.0	3.75
6	0.0	4.53
7	0.0	3.39
8	0.0	2.18
9	0.0	2.30
10	0.0	5.15
AVG.	0.0	3.55

The fabric sample submitted meets the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Karon S. Matkins
Karon S. Matkins

UM/mr
Attachment